

Specification for Debris net

We hereby certify that following data of specification is correct and true.

Item	Actual measurement value
Weight	60 gsm
Material	100% pure High Density Polyethylene
FR treated	NFPA 701 method 2 standard
Yarn diameter	0.15 mm
Denier	189 D/A
Tolerance of weight	+/- 5%
Yarn tenacity	965 Gram
Warp	8 wale
weft	7 course

Dated July19h, 2022

Certified by General director of:



TEST REPORT

APPLICANT : _____).

REPORT NO. : J270-17-00536

SAMPLE RECEIVED DATE : 2017-09-12

REPORT ISSUED DATE : 2017-09-18

PAGE : 1 OF 2

DESCRIPTION : ONE(1) PIECE OF SUBMITTED CUTTING SAID TO BE NET.



=====

BUYER'S NAME : Rolathene LTD

ITEM : PE Debris net (Blue FR) , RLT17-1A,B

=====

TEST CONDUCTED : AS REQUESTED BY THE APPLICANT, FOR DETAILS PLEASE SEE ATTACHED PAGES.

PREPARED AND CHECKED BY
FOR FITI
SANG SOO, HAN
QUALITY MANAGERAUTHORIZED BY
FOR FITI
YOUNG-CHAN KIM
PRESIDENT

✱ Report Verification No.: 1IH6-JV89-MKY4 ✱

(You can see the authenticity of your test report through the above "Report Verification No." at FITI homepage.)

e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI.

REPORT NO.: J270-17-00536
PAGE : 2 OF 2

01. FLAMMABILITY (NFPA 701 : 2015, TEST METHOD 2(FLAT))

#1

	ORIGINAL		
	AFTER FLAME TIME (s)	DRIP BURN (s)	CHAR LENGTH (mm)
1	0	0	215
2	0	0	219
3	0	0	230
4	0	0	221
5	0	0	204
6	0	0	209
7	0	0	227
8	0	0	214
9	0	0	211
10	0	0	208
AVG.	0	0	216

NOTE) · CONCLUSION : BASED UPON THE RESULTS OF THE TEST REPORT, THE SUBMITTED SAMPLE MEETS THE PERFORMANCE REQUIREMENTS AS STATED IN NFPA 701, TEST METHOD 2(2015).

· ACCEPTANCE CRITERIA

AFTER FLAME TIME (s)	DRIP BURN (s)	CHAR LENGTH (mm)
MAX. IND. < 2	MAX. IND. < 2	MAX. IND. < 435

· TEST WAS CONDUCTED ONLY IN THE ORIGINAL STATE BY THE CLIENT'S REQUEST.

** End of The Report **

SAMPLE :

e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI. This test report is irrelevant to KOLAS accreditation.