SINOPS LIMITED

1 Mill Pool, Nash Lane, Belbroughton, Stourbridge, West Midlands DY9 9AF



TECHNICAL DATA SHEET

STEEL BANDING
VJT Codes: 23600010, 23600033 & 23600040

We confirm our Steel Banding is cold rolled and heat treated, finished with black paint and then waxed and de-burred. It is tensional, ribbon wound (pancake), technical information as follows:-

| VJT Code | 23600010 | 23600033 | 23600040 |
|-----------------------------|-------------------|-------------------|-------------------|
| Supplier Code | 2281500 | 2281520 | 2281540 |
| Name (Size) | 13mm | 16mm | 19mm |
| Coil Weight (approx.) | 16Kg +/- 0.5Kg | 20Kg +/- 0.5Kg | 24Kg +/- 0.5Kg |
| Strap Width | 12.7mm +/- 0.15mm | 15.9mm +/- 0.15mm | 19.0mm +/- 0.15mm |
| Strap Thickness | 0.5mm +/- 0.035mm | 0.5mm +/- 0.035mm | 0.5mm +/- 0.035mm |
| Outside Coil Diameter | 550mm | 550mm | 550mm |
| Inside Coil Diameter | 300mm | 300mm | 300mm |
| Coil Length | 320m +/- 5% (16m) | 320m +/- 5% (16m) | 320m +/- 5% (16m) |
| Average Breaking Load (mpa) | 850mpa | 850mpa | 850mpa |
| Average Breaking Load (N) | 5,390 | 6,750 | 8,070 |
| Average Elongation (A5) | 4% | 4% | 4% |

Please note: This product is supplied in packs of 2 coils.

This data sheet is valid until there is a significant change in the product and its characteristics.

igned by: Position: Commercial Manager Name: Andy Bridge Date: 17 February 2022

