



Silicone Remover

Product description

Silicone Remover is a ready to use and fast-working product based on hydrocarbons for removing cured silicone and ms polymers.

Properties

- Fast acting
- Does not drip
- Specifically for silicones and hybrid polymeres

Applications

- Removal of old silicone residue, spilled silicone or spilled MS polymeres from different kind of surfaces.
- Removes all residue of spilled silicone.

Technical data

Base	Hydrocarbon solvents
Consistency	Stable gel
Density	ca. 0.87 g/ml
Application temperature	+5°C → +30°C



Substrates

- Substrate condition
Dry
- Substrate types
Silicone Remover is compatible with following substrates: metals, ceramic tiles, laminated plate, glass, etc.. Silicone Remover has no good adhesion or is not suitable for Nylon, PMMA. We recommend a preliminary compatibility test on every surface.

Application method

- Application method
Remove the cured sealant as much as possible using a sharp knife. Shake the canister thoroughly and apply Silicone Remover on the surface to be cleaned. Leave to work for at least 10 minutes. Clean Silicone Remover and remove softened remnants of sealant with a knife, spatula, or a rough cloth. Repeat if necessary. Wash thoroughly with water to avoid surface degradation.

Health- and Safety Recommendations

Use only in well-ventilated areas.
In case of contact with eyes, wash immediately with plenty of water.
Always wear gloves and goggles.
In case of contact with skin, wash with water and soap.
Dangerous. Respect the precautions for use.

Packaging/Logistics

Colour: Please consult the product catalogue, the Soudal website or a Soudal representative.
Packaging: Please consult the product catalogue, the Soudal website or a Soudal representative.



Silicone Remover

Shelf life: 5 years in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C

Remarks

- Silicone Remover can cause staining on porous surfaces.
- Due to the wide variety of possible plastics and paints and to avoid damage to the surface, a preliminary compatibility test is recommended.
- After Silicone Remover dries, a white haze may appear, which can be removed with water and, if needed, soap

This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. It is general in nature and does not constitute any liability. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application. In every case it is recommended to carry out preliminary experiments. The manufacturer reserves the right to modify products without prior notice.