

# Sinops Limited

1 Mill Pool, Nash Lane, Belbroughton, Stourbridge, West Midlands, DY9 9AF



## DATA SHEET

### STEEL BANDING

We confirm our Steel Banding is cold rolled and heat treated. It is tensional, ribbon wound (pancake)

Code	23600010	23600033	23600040
Alt Code	2281500	2281520	2281540
Name	13mm	16mm	19mm
Coil Weight (approx.)	16Kg	20Kg	24Kg
	(+/- 0.5Kg)	(+/- 0.5Kg)	(+/- 0.5Kg)
Finish	Black Painted & Waxed		
Edges	Deburred		
Strap Width	12.7mm	15.9mm	19.0mm
	(+/- 0.15mm)	(+/- 0.15mm)	(+/- 0.15mm)
Strap Thickness	0.5mm	0.5mm	0.5mm
	(+/- 0.035mm)	(+/- 0.035mm)	(+/- 0.035mm)
Outside Coil Diameter	550mm	550mm	550mm
Inside Coil Diameter	300mm	300mm	300mm
Coil Length	320m +/- 5% (16m)		
Average Breaking Load (mpa)	850mpa	850mpa	850mpa
Average Breaking Load (N)	5,390	6,750	8,070
Average Elongation (A5)	4%	4%	4%

This data sheet is valid until there is significant change in the product and characteristics.

Signed By:

Name:

*Andy Bridge*

Position: *Commercial Manager*

Date:

*05 October 2020*