



Yeşilbayır Mah. Şimşir Sk. No: 22 Hadımköy - İstanbul/TÜRKİYE Tel: 0212 771 13 71 Fax: 0212 771 38 88

P625 CONSTRUCTION PU SEALANT

Akfix P625 is a one-component, low-modulus polyurethane sealant that cures on exposure to atmospheric humidity. It possesses excellent adhesion to all typical construction materials such as cement based materials, brick, ceramic, glass, wood, galvanized and painted sheet iron and various plastics.

FEATURES & BENEFITS

- Possesses permanent elasticity
- 25 % movement capability
- No surface tackiness after full cure.
- Do not pick up dirt
- No shrinkage
- Cures bubble-free
- Enhanced storage stability
- No sagging Thixotropic
- Can be applied with hand gun and tooled easily
- Paintable

APPLICATION AREAS

- Expansion joints between many different construction materials
- Bonding of roof tiles
- Installation of PVC window frames
- Connection joints between wood window- and doorframes and walls
- Joints between prefabricated construction materials
- Sealing and bonding of ventilation ducts, gutters and spouts etc.
- For expansion joints between pre-cast concrete panels

INSTRUCTIONS

- Before application, be sure that joint surfaces are clean, dry and free of all contamination,
- Apply sealant evenly, If necessary, use masking tape and remove the tape while the sealant is still soft.
- Joint width/depth ratio should be 2:1 (Table 1),
- If necessary, use back up material to adjust joint depth,
- Sealants should adhere to only two surfaces of the joint: Use backer rods and bond breakers to facilitate.



Provides Good Elastic Mechanical Resistance



Yesilbayır Mah, Simsir Sk. No: 22 Hadımköy - İstanbul/TÜRKİYE Tel: 0212 771 13 71 Fax: 0212 771 38 88

www.akfix.com - info@akfix.com

Consumption (approx.)

TECHNICAL

Joint width	15 mm	20 mm	25 mm	30 mm	35 mm
Joint Depth	8 mm	10 mm	12 mm	15 mm	15 mm
Joint length / 600 ml	5 meters	3 meters	2 meters	1,3 meters	1,1 meters

Surface Preparation

Following cleaning procedure and materials are recommended:

Glass	Degrease with alcohol or MEK	
Aluminium, light alloys and stainless steel	Degrease with alcohol or MEK	
Other Metals	Lightly abrade then degrease as above	
Wood	Lightly abrade surface then remove dust	
Plastics	Degrease using an agent recommended by plastics manufacturer	
Concrete and other alkaline Surfaces	Brush and remove dust	

STANDARDS

Meets or exceeds the requirements of the following specifications:

- The requirements of VOC content specifications in LEED credit EQc4.1 "Low-emitting products" of SCAQMD rule 1168.
- The French VOC requirements for class A+
- CE marked for EN 15651 for façade applications.

RESTRICTIONS;

- It must not be used in totally confined spaces where sealant cannot cure due to lack of atmospheric moisture.
- Do not use in applications where continuous water immersion is possible.
- Do not apply on frozen or wet surfaces or through standing water.
- Prolonged exposure to direct sunlight can cause discoloring,
- Avoid application below 5 °C and above 40 °C.



Yeşilbayır Mah. Şimşir Sk. No: 22 Hadımköy - İstanbul/TÜRKİYE Tel: 0212 771 13 71 Fax: 0212 771 38 88 🄰 www.akfix.com - info@akfix.com

STORAGE AND SHELF LIFE;

TECHNICAL

DATA

SHEET

15 months if stored in its original package, away from direct sunlight and moisture, between +10 °C and +25 °C

SAFETY & DISPOSAL

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

PROPERTIES

BEFORE CURING				
Basis	: Polyurethane			
Consistency	: Thixotropic			
Curing Mechanism	: Moisture Curing			
Density	: 1,20±0,03 g/ml			
Tack free time	: 30-60 min (23°C and 50% R.H)			
Curing Rate	: Min. 2,00 mm/ day (23°C and 50% R.H)		
Sagging	: 0 mm	(EN ISO 7390)		
Temperature Resistance	: -40°C to +70°C			
Application Temperature	: +5°C to +40°C			

AFTER CURING				
Hardness Shore A	: 25-30	After 28 days		
Paintibility	: Yes *			
Elastic Recovery	:≥ 70%	(ISO 7389)		
Movement Capability	:25 %			
Glass-Glass				
Elongation at break	: min.120%	(ISO8339)		
E100 Modulus (23 °C)	: 0.30-0.40 N/mm ²	(ISO8339)		
E100 Modulus (-20 °C)	:≤ 0,60 N/mm²	(ISO8339)		
DUMBLE TEST				
Elongation at break	: ≥%700			
Tensile Strength	: 1.0-1.5 N/mm²			





Yesilbayır Mah. Simsir Sk. No: 22 Hadımköy - İstanbul/TÜRKİYE Tel: 0212 771 13 71 Fax: 0212 771 38 88

www.akfix.com - info@akfix.com

PRODUCT

Product Type	Volume	Package
White/ Black/ Grey	310 ml	12
White/Black/Grey (Sausage)	600 ml	12

DISCLAIMER

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in maccordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.