



Kirk Sandall Industrial Estate, Doncaster, South
Yorkshire, DN3 1QR

+44 (0)1302 310 113
enquiries@prosolveproducts.com
www. prosolveproducts.com

ProSolve is trademark of S.T.L Trading Company
Limited
Reg in England No: 5230722
VAT Reg No: 381 3533 58

PRODUCT DATASHEET

ProSolve Anti Corrosive Primer (OXPG5 and OXPR5) 5L

DESCRIPTION

A tough, quick air drying anti corrosive paint suitable for direct to metal priming applications. Easy to apply by spray, roller and brush.

PRODUCT AND TECHNICAL DETAILS

STANDARD COLOURS	Red, Grey
DRY FILM APPEARANCE	Matt finish
SPREADING RATE	5.5 TO 8 m2 /litre
SURFACE DRY @20°C	15 - 30 Minutes
RECOATING TIME @20°C	1 Hour
TYPICAL WET FILM THICKNESS	120– 160 Microns
TYPICAL DRY FILM THICKNESS	65 - 90 Microns
SOLIDS BY VOLUME	56% (ASTM D2697)
V.O.C INFORMATION	430 g/litre (from formula to satisfy EU Solvent Emissions Directive) 344g/kg (from formula to satisfy EU SED regulations)
APPLICATION TEMPERATURE	10 – 35 degrees C
APPLICATION METHODS	Spray (airless spray, air assisted spray 15-17 thou tip), Brush, Roller
SUBSTRATES	Suitably cleaned & dry surfaces
FLASH POINT	25°C
SHELF LIFE	24 Months

PRODUCT FEATURES:

Tough anti corrosive primer, spray/brush/roller application, easy to use.

This product is a good quality, quick drying, anti corrosive primer made from high quality alkyd resins, formulated for airless spray and is free from heavy metals.

IMPORTANT NOTICE

All statements, technical information and recommendations are based on tests we believe to be reliable as at the date of hereof, but the accuracy or completeness thereof is not guaranteed. Please ensure before using the product that it is suitable for your intended use. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, other than for fraudulent misrepresentation, ProSolve expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information.